

DF1100 and DF1200

CHEMFILM® DF1100 is a multilayer cast PTFE film, fully fused, with one surface modified to render it receptive to many conventional adhesives, elastomers, resins and potting compounds. The surface treatment was developed to assure that its application over pure PTFE would not degrade or discolor the basic film. After surface treatment, the PTFE film loses none of its excellent physical and electrical characteristics, except that the surface treatment results in a natural color which does not affect any of the desired properties. CHEMFILM type DF1200 is DF1100 laminated to 2 mils of acrylic pressure sensitive adhesive.

FEATURES	BENEFITS
Cast Film	<ul style="list-style-type: none"> Uniform tensile properties in both machine and traverse direction Isotropic shrinkage as a function of temperature
Multilayer	<ul style="list-style-type: none"> The unique bonding layer will adhere to a variety of adhesives and elastomers while the other surfaces maintain all the properties of PTFE Pigments and other additives may be added to individual layers to customize performance
PTFE	<ul style="list-style-type: none"> Superior performance in a wide range of chemical, thermal and electrical environments
Slitting	<ul style="list-style-type: none"> Available in slit widths to 1", supplied in pad rolls; minimum quantities apply

Typical Properties

	Method	Value
MECHANICAL		
Tensile Strength (psi)	ASTM D882-54T	4,300
Elongation (%)	ASTM D882-54T	400
Elastic Modulus (psi)	ASTM D882	60,000
Coefficient of Friction	ASTM D194	0.2
ELECTRICAL		
Dielectric Constant, 60-10 ⁸ Hz	ASTM D150	2.0
Power/Dissipation	ASTM D150	0.009
Surface Resistivity	ASTM D257	2.0 x10 ¹⁷
Volume Resistivity	ASTM D257	>10 ¹⁵
Dielectric Strength (volts/mil)	ASTM D149	4,200
Surface Arc Resistance	ASTM D495	Does not arc
Product Number	DF1100	DF1200
Available Gauge (mil)	1.0-5.0	1.0-5.0 (base film w/o adhesive)
Colors	On request	On request
Continuous Service Temp.	+500°F, -400°F +260°F, -188°F	+300°F, -100°F +140°F, -90°F

Values shown are typical. Certified test reports for writing specifications are available.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. Saint-Gobain assumes no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. Saint-Gobain warrants that the material itself does not infringe any United States patent, but no license is implied nor is any further warranty made.

Saint-Gobain Performance Plastics Corporation
 14 McCaffrey Street
 Hoosick Falls, NY 12090
Customer Service: (800) 962-2666
 Tel: (518) 686-7301
 Fax: (800) 526-8479, (518) 686-4840
www.plastics.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHEMFILM is a registered trademark.

©2002 Saint-Gobain Performance Plastics Corporation
 AFF-1150-PDF-0902-SGCS